

Cable Products

Reinforced nonwoven waterblocking tape

DATA SHEET

3C1152

Properties (23°C, 50% RH)	Nominal value	Unit	Test methods = LANTOR® method
Mass per unit area	147	g/m ²	ISO 9073-1 = KE030
Thickness	0.40	mm	ISO 9073-2 = KE050
Tensile strength	115	N/cm	ISO 9073-3 = KE060
Elongation	13	%	ISO 9073-3 = KE060
Surface resistance		Ω/[]	IEC 167 = KE200
Volume resistivity	0.3	MΩ.cm	DIN 54345, Part 1 = KE276
Moisture content (ex works)	5	%	110°C (halogen drying) = KE186
Swelling speed (first min.)	9.5	mm/min.	Eur. HD 605 S1/A1 = KE100
Swelling height (final in 3 min.)	12	mm	Eur. HD 605 S1/A1 = KE100
Max. service temperature	100	°C	IEC 216 = Info Sheet 45, Para. 11
Max. processing temperature	225	°C	Info Sheet 45, Para. 12
Composition	Polyester Polyacrylate Waterswellable powder / Carbon impregnation / Polyester scrim		

Used in power cables, in the screen area, over the open metal screen (wire)

This information is presented in good faith but is not warranted as to the accuracy of the results.
Also, freedom from patent infringement is not inferred.

This information is offered solely for your investigation, verification and consideration.